

DRIVING SURFACE PERFECTION

ACID#8

TECHNICAL DATA SHEET

Acid Etch Primer

TECHNICAL DATA SHEET & PROCESS GUIDE

ACID #8 is a 1K ready to use etch primer available in 1 litre cans. It is used for priming bare metal surfaces, this promotes adhesion of paint and prevents steel from rusting.

ACID #8 is chromate free. Typical applications are over rub through areas prior to painting, on new bare metal panels or over bare seams before sealant is applied.

PROPERTIES ACID#8 can be applied to the following surfaces:-Bare metal such as steel, zinc galvanised and aluminium Can be air dried or low baked **Available Colours** Grey **TECHNICAL DATA** Galvanised Substrates Aluminium Mild Steel Viscosity 34 - 38 seconds BS4 Specific gravity g/cm³ 1.03 **APPLICATION GUIDE Tools Required** Degreaser Abrasives HVLP Gravity Gun **Painters Overalls** Substrate Preparation To achieve best results, good preparation is essential. Degrease with U-POL Precleaner (S2000, S2001 or S2002). Abrade the surface: Bare Metal (mild steel): abrade with P180 - P240

Aluminium and zinc coated steel: P180 - P240

Before applying primer, clean lightly once more with SYSTEM 20 Degreasers and dry thoroughly.



DRIVING SURFACE PERFECTION

TECHNICAL DATA SHEET

ACID#8

Acid Etch Primer

TECHNICAL DATA SHEET & PROCESS GUIDE

Viscosity Poise Working Pot-Life @ 20°C		34 - 38 seconds BS4 n/a
Compliant HVL	P Gravity Gun Gun tip size Air Pressure at the gun	1.2- 1.3mm 1.8 - 2.0 bar The product can be thinned up to 5% with alcohol, e.g. IMS/Butanol. Equipment can be cleaned with an alcohol based thinner.
Coats	Build / microns	1 - 2 coats approx 20 - 30
Flash-off @ 20°	C Between coats	3 - 5 mins
Drying Times	overcoat time@ 20°C	10 - 20 mins
Over Painting	Inder normal circumstances	it is not necessary to flat $ACID$ #8 and can be directly



Over Painting Under normal circumstances it is not necessary to flat ACID #8 and can be directly overcoated. ACID #8 may be overcoated directly with top coat. However, if the repair requires additional build primer filler should be used before topcoat is applied.



DRIVING SURFACE PERFECTION

TECHNICAL DATA SHEET

ACID#8

Acid Etch Primer

TECHNICAL DATA SHEET & PROCESS GUIDE STORAGE & VOC INFORMATION



2 years from date of manufacture in sealed original containers.
Recommended Storage Temperature 5°C - 25°C
Equipment Cleaning Equipment can be cleaned with an alcohol based thinner.

VOC Information



The EU limit for this product (product category: IIBc) in ready to use form is 780g/litre. The VOC content of this product in ready to use form is 717g/litre.

Order Code	Format	Colour
ACID/1	1L Tin	Grey Primer

IMPORTANT: FOR PROFESSIONAL USE ONLY. Read full instructions before use.

This product contains hazardous materials and therefore appropriate personal protective equipment should always be used. Please refer to the label and consult the safety data sheet for full handling instructions and personal protection information. U-POL disclaims any liability where the user does not wear the recommended personal protective equipment. The above data is for information only and may change without prior notice. It is the Buyers responsibility to ensure the suitability of the products for their own use and check the information is up to date. The recommendation of use of our products and application in our technical data sheets are based on our knowledge and experience. These data sheets are available via your local stockist or via the U-POL website at WWW.U-POL.COM. U-POL is not responsible for the results obtained by others over whose methods we have no control and thereof U-POL is not liable for consequential or incidental damages including loss of profits.

U-POL Ltd

4th Floor, The Grange, 100 High Street London, N14 6BN WWW.U-POL.COM

UK Sales T: +44 (0)20 8492 5920 F: +44 (0)20 8150 5605

uk.sales@u-pol.com

International T: +44 (0)20 8492 5900 F: +44 (0)20 8150 5605 sales@u-pol.com Technical T: +44 (0)1933 230 310 F: +44 (0)1933 425 797 technicaldepartment@u-pol.com