






TECHNICAL DATA SHEET

EZ ULTRA LITE

10134

<p>DESCRIPTION & USE:</p>	<p>EVERCOAT EZ ULTRA LITE is a deep filling, smooth spreading, easy levelling, and ULTRA easy sanding filler that offers excellent adhesion and feather edge to steel, galvanized steel, and aluminum.</p> <p>Blue cream hardener included.</p>
<p>STORAGE:</p>	 <p>Store in accordance with local regulations. Observe label precautions. Do not store above the following temperature: 25°C (77°F). Store in a cool, well-ventilated area away from incompatible materials and ignition sources. Keep away from: oxidizing agents, strong alkalis, and strong acids. No smoking. Prevent unauthorized access. Containers that have been opened must be carefully resealed and kept upright to prevent leakage. Do not empty into drains. Never return mixed product back into container.</p>
<p>PREPARATION:</p>	 <p>Clean surface. Remove all dirt, oil grease and wax. Use p80—p180grit abrasives to remove and sand paint. Thoroughly clean surface using a suitable surface cleaner such as a solvent or water based panel preparation solution. Surface must be completely dry before application.</p>
<p>MIXING:</p>	 <p><i>Use with Cream Hardener Only!</i> Place desired amount of putty on a clean, non-fibrous/non-porous mixing board</p> <p>Add hardener in a ratio of 100 parts EVERCOAT EZ ULTRA LITE to 2 parts EVERCOAT CREAM HARDENER by weight. EXAMPLE: For a 50mm diameter puddle of filler add a bead of cream hardener from the centre to the edge of the puddle. For a 100mm diameter puddle add a bead of hardener from edge to edge across the centre of the puddle. Puddles larger than 100mm in diameter will require additional hardener. Mix thoroughly until a uniform colour is achieved.</p>
<p>APPLICATION:</p>	 <p>Spread a thin layer of mixed materials over surface using firm pressure to ensure best adhesion. Apply additional layers building area slightly higher than the surface to allow for sanding.</p>
<p>FINISHING:</p>	 <p>Sand and shape the body filler with P80 – P180 grit abrasive. Avoid coarse sand scratches outside of the filler area during the initial cut. Finish sand body filler with P180-grit. For best results, apply a skim coat of EVERCOAT EASY SAND™ putty over the repair. This will provide a smoother finish and reduce the number of coats of primer required for a quality finish.</p>

TECHNICAL DATA SHEET

EZ ULTRA LITE

10134

TECHNICAL SPECIFICATIONS:	Colour	Grey
	Physical State	Paste
	Pot Life	3 – 5 minutes
	Sand Time	15 – 20 minutes
	Viscosity	150,000 to 250,000 cps
	Corrosion Resistance	500 hours Harsaw salt Spray Cabinet
	Water Resistance	No Blistering, wrinkling or softening after 24 hours immersion
	Maximum Allowable Heat (coated)	126.6°C (260°F) Surface Temperature
	Max. Recommended Thickness (sanded)	6.3mm
	Contents and Caution	SDS Available on request
	VOC	Refer to Section 9 of the Safety Data Sheet
Properties are typical values and should not be considered as sales specifications. Physical testing performed at approximately 25°C (77°F)/ 75% RH unless otherwise noted.		
SAFETY & HANDLING:	Read all directions and warnings prior to using Evercoat products. Safety Data Sheets can be found online at evercoat.com.	

Batch Identification

Evercoat products are identified with their original batch code and date of manufacturing that includes: the year, the month and the specific production batch. The batch code is located on the bottom part of the product label or underneath the bottom of the container.

Example 1: **103622**

Example 2: **411437**

Year Month – Batch
1 03 622
 2011 March Batch

Year – Month – Batch
4 11 437
 2014 November Batch