

# S2080

#### **2K SUPERIOR HS CLEARCOAT 2:1 MIX**

### **TECHNICAL DATA SHEET & PROCESS GUIDE**

U-POL S2080 is a HS 2K acrylic clearcoat, it can be applied unthinned or thinned up to 10% with S2040 range of thinners.

### **PROPERTIES**

- Good flow and non-sag properties
- Hardens rapidly to give a high build UV resistant coating

**Viscosity** 

- Has excellent gloss and long term durability
- Can be air dried, low baked or IR Cured
- Can be easily polished once cured

### **TECHNICAL DATA**



**Substrates** 

Manufacturers basecoat, solvent or waterbased

Base Mixed 15 - 17 s/ DIN 4 44.00% 41.50%

 Solid content
 44.00%
 41.50

 Specific gravity g/cm³
 0.97
 0.98

## APPLICATION GUIDE



### **Tools Required**

SYSTEM 20™ Degreaser

HVLP Gravity Gun

MAXIMUM Abrasives

MAXIMUM Painters Overalls

### **Hardener Selection**

Please note this product is compatible with the S2030 to S2033 range

Temperature ºC	Hardener
-5 -15°C	S2031
5 - 25°C	S2030
15 - 35°C	S2032
25 - +40°C	S2033



### **Substrate Preparation** □

Dried waterbased or solvent based basecoat to the manufacturers instructions

To achieve best results, good preparation is essential. Degrease with U-POL Precleaner (S2000, S2001 or S2002). Abrade the surface:

Original cured paint: wet flat with P800 - P1000 or dry P600 - P800.



# S2080

#### **2K SUPERIOR HS CLEARCOAT 2:1 MIX**

## **TECHNICAL DATA SHEET & PROCESS GUIDE**



**Mixing Ratio** 

Standard Application

**\$2080:**Hardener **2**:1

Mixing by Weight (grams)

**S2080** 200 **S2032** 102



Viscosity DIN 4 / sec

Working Pot-Life @ 20°C 4 - 6 hours



**Compliant HVLP Gravity Gun** 

Gun tip size 1.2 - 1.4mm

Air Pressure at the gun 2



Coats

2 coats

15 - 17

Build / microns 50



Flash-off @ 20°C

Between coats 5 - 10 mins



**Drying Times** 

Tack free @ 20°C 60 min

Through dry @ 20°C 12 - 14 hours

Through dry @ 60°C 30 mins



# S2080

#### **2K SUPERIOR HS CLEARCOAT 2:1 MIX**

# TECHNICAL DATA SHEET & PROCESS GUIDE STORAGE & VOC INFORMATION



**Shelf Life** 

2 years from date of manufacture in sealed original containers.

**Recommended Storage Temperature** 5°C - 25°C

**Equipment Cleaning** Clean gun Immediately after use with SYSTEM 20 thinner or

gunwash.

Important Remarks□

Do not use activated product beyond pot life.

Activated material should not be returned to the original can of non-activated material.



#### **VOC Information**

This product is not to be used for automotive repair within the EU

Ready to use VOC g/I

	Colour	
	clear	540

### IMPORTANT: FOR PROFESSIONAL USE ONLY. Read full instructions before use.

This product contains hazardous materials and therefore appropriate personal protective equipment should always be used. Please refer to the label and consult the safety data sheet for full handling instructions and personal protection information. U-POL disclaims any liability where the user does not wear the recommended personal protective equipment. The above data is for information only and may change without prior notice. It is the Buyers responsibility to ensure the suitability of the products for their own use and check the information is up to date. The recommendation of use of our products and application in our technical data sheets are based on our knowledge and experience. These data sheets are available via your local stockist or via the U-POL website at WWW.U-POL.COM. U-POL is not responsible for the results obtained by others over whose methods we have no control and thereof U-POL is not liable for consequential or incidental damages including loss of profits.

U-POL Ltd

4<sup>th</sup> Floor, The Grange, 100 High Street London, N14 6BN

WWW.U-POL.COM

**UK Sales** 

T: +44 (0)20 8492 5920 F: +44 (0)20 8150 5605

uk.sales@u-pol.com

International

T: +44 (0)20 8492 5900 F: +44 (0)20 8150 5605

sales@u-pol.com

Technical

T: +44 (0)1933 230 310 F: +44 (0)1933 425 797

technicaldepartment@u-pol.com

U-POL S2080 -TDS - EN-NEW Edition # 1; 06/07/2017 3/3