



Product Flash VOC Clear coat

Colour Transparent

Product description Fast drying 2K UHS Clear coat. Easy to use with excellent flowing abilities and a high gloss

finish. Use it for single spare parts or complete cars, it is one clear for all!

Use for Single parts or complete paint jobs in the automotive repair industry.

Resin Acrylic resin

Substrate After the Water- or Solvent borne Base coat flashed off it can be

covered with the Flash VOC Clear coat. In-between 24 hours the clear can be resprayed

without sanding.

Application To use with common spray guns (SATAjet, Iwata, DeVilbiss etc.)

Gravity cup spray gun RP: 1.2-1.4 mm 2-2.5 bar at 15-20 cm distance to the painting object

Gravity cup spray gun HVLP:

1.2-1.3 mm 2 bar at 10 cm distance to the painting object Layers: 1,5 or 2 full coats with 5 min flash-off in-between.

Viscosity 18-19 sec 4mm/DIN

Mixing ratio 2:

Hardener Flash Hardener Fast 86010 - 2,5 L / 500 ml
Pot life ca. 1,5 hours/20 °C with Flash Hardener Fast
ca. 1 hour/20 °C with Flash Hardener Fast

Drying time 10 min/50 °C or 20 min/20 °C with Flash Hardener Standard.

5 min/50 °C or 15 min/20 °C with Flash Hardener Fast

Polishing After baking and cool down it is direct polishable

Film Build 50-60 m

VOC 2004/42/EC - IIB(d)(420) 410g/F

Standard packaging 1L / 5

Shelf life 18 months in original packaging. Store it cool and dry and protect against daylight.

+5 °C - +30 °C

Information given in this sheet represent the best of our knowledge.

Please verify before use if this product is suitable for your application.





The Future is here Triple A Grade Low Energy Clear Dry time 15 mins @ 20 °C





Made in Germany